

Wet Chopped Strands

Wet chopped strands are produced from continuous filament strands and are used as raw materials for fiberglass paper. Products produced include wet-laid mat which have found wide use in building materials and in electrical applications. Applications are battery separators and asphalt felts.



Properties

- ✓ Quick and easy dispersion in pulp and slurry

Specifications

- Filament diameter: 7 to 13microns
- Loss on Ignition: 0.5 %
- Cut Length 6, 12, 20 and 25mm (1/4", 1/2", 3/4" and 1")
- Available in E-Glass and C-Glass
- Packaging: 22 kg/bag (49 lbs), 45 bags/pallet, 20 pallets / 20ft container

Technical Characteristics					
Product Number	Glass Type	Filament Diameter (μ)	Size Content (%)	Moisture Content (%)	Cut Length (mm)
WCS-1	E	7	0.25 \pm 0.10	5 - 10	6 - 24
WCS-2	E	9	0.25 \pm 0.10	5 - 10	6 - 24
WCS-3	E	11	0.25 \pm 0.10	5 - 10	6 - 24
WCS-4	E	13	0.25 \pm 0.10	5 - 10	6 - 24
WCS-5	C	12	0.20 \pm 0.10	10 - 15	6 - 24